

### PR-1782 Class S, low density sprayable sealant

#### Description

PR-1782 Class S is a low density sprayable sealant with a service temperature range of -55°C (-67°F) to 130°C (266°F). This material is designed for sealing integral fuel tanks and pressurised cabins. The cured sealant maintains excellent elastomeric properties after prolonged exposure to jet fuel, aviation gas and phosphoric ester hydraulic fluids.

PR-1782 Class S is a three-part, manganese dioxide cured polysulfide compound. Once mixed, the uncured material has a fluid consistency suitable for application by brush or spray. It cures at room temperature to form a resilient sealant having excellent adhesion to common aircraft substrates.

#### Application properties (typical)

|   |                                      |                                   |
|---|--------------------------------------|-----------------------------------|
| Colour  |                                      |                                   |
| Part A  | Blue                                 |                                   |
| Part B  | Black                                |                                   |
| Part C  | Colourless                           |                                   |
| Mixed   | Grey                                 |                                   |
| Mix Ratio<br>by weight                                    | Part A: Part B: Part C<br>70: 10: 30 |                                   |
| Base viscosity,<br>(Brookfield #5@10rpm)<br>Pa.s, (poise) | 2-10 (20-100)                        |                                   |
| Application life and cure time at 23°C (73°F), 50% RH     |                                      |                                   |
| Application<br>life<br>(hours)                            | Tack free<br>time<br>(hours)         | Time to 30<br>shore A*<br>(hours) |
| 2   | 10                                   | 48                                |

\*Instantaneous hardness measurement

#### Performance properties (typical)

|  |       |
|--|-------|
| Standard cure 14 days @ 25°C (77°F), 50% RH  |       |
| Cured specific gravity   | <1.35 |
| Non-volatile content, %  | >60   |
| Ultimate cure hardness, Shore A  | 30-50 |
| Peel Strength, N/mm, 100% cohesive failure<br>No exposure<br>P60   | 75    |
| Resistance to fluids: excellent resistance to water, alcohols, synthetic and petroleum-based lubricating oils, and petroleum-based hydraulic fluids. |       |
| Low-temperature flexibility @ -55°C (-67°F) – no cracking, checking or loss of adhesion.   |       |

**Note:** The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

#### Surface preparation

Immediately before applying sealant to primed substrates, the surfaces should be cleaned with solvents. Contaminants such as dirt, grease, and/or processing lubricants must be removed prior to sealant application. A progressive cleaning procedure should be employed using appropriate solvents and a new lint-free cloth. (Reclaimed solvents or tissue paper should not be used).

Always pour solvent on the cloth to avoid contaminating the solvent supply. Wash one small area at a time. It is important that the surface is dried with a second clean cloth prior to the solvent evaporating to prevent the redeposition of contaminants on the substrate

Substrate composition can vary greatly. This can affect sealant adhesion. It is recommended that adhesion characteristics to a specific substrate be determined prior to application on production parts or assemblies.

For a more thorough discussion of proper surface preparation, please consult the SAE Aerospace Information Report AIR 4069. This document is available through SAE, 400 Commonwealth Avenue, Warrendale, PA 15096-0001.

## PR-1782 Class S, low density sprayable sealant

### Mixing instructions

PR-1782 Class S is supplied in a three-part kit. Mix according to ratios indicated in the application properties section. Mix part A and part B separately to uniformity, then pour all the diluent (part C) into the base (part A). Mix thoroughly until homogeneous. Add all the accelerator (part B) and mix thoroughly for approximately 7 – 10 minutes until homogeneous. Take care to avoid leaving unmixed areas around the sides or bottom of the mixing container.

CAUTION: Do not mix accelerator with the base until ready to use.

### Storage life

The storage life of PR-1782 Class S is 6 months when stored in original, unopened containers at temperatures between 4-27°C (39-81°F). During storage, slight variations in the application characteristics may occur. This does not affect either the overall application properties or the final performance properties of the product.

### Health precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**For emergency medical information call:  
1-800-228-5635.**

**Additional information can be found at:  
[www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call:  
1-800-AEROMIX (2376649).**

**Semkit is a trademark of PRC-DeSoto International Inc., registered with the U.S. Patent Office.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International,  
Inc. 12780 San Fernando  
Road Sylmar, CA 91342  
Telephone (818) 362-6711  
Toll Free (800) AEROMIX  
[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 19/06/19  
Supersedes: New  
Lit: 4673